

IN THE CLAIMS:

Please amend the claims as follows:

1-4. (canceled)

5. (added) An electrolyte membrane/electrode assembly of a solid

polymer electrolyte fuel cell, comprising an electrolyte membrane, and an air pole and a

fuel pole provided to sandwich said electrolyte membrane therebetween, each of said

electrolyte membrane, said air pole and said fuel pole including a polymer ion-exchange

component, wherein said polymer ion-exchange component is a sulfonated substance

of aromatic hydrocarbon polymer, said electrolyte membrane/electrode assembly has

an ion-exchange capacity  $I_c$  in a range of  $0.9 \text{ meq/g} \leq I_c \leq 5 \text{ meq/g}$ , and a dynamic

viscoelastic modulus  $D_v$  at  $85^\circ\text{C}$  in a range of  $5 \times 10^8 \text{ Pa} \leq D_v \leq 1 \times 10^{10} \text{ Pa}$ , and

wherein if the weight of catalyst particles included in each of said air pole and said fuel

pole is represented by  $W$ , and the weight of said polymer ion-exchange component

included in each of said air pole and said fuel pole is represented by  $X$ , the ratio  $X/W$  of

the weights  $W$  and  $X$  is in a range of  $0.05 \leq X/W \leq 0.80$ .

6. (added) An electrolyte membrane/electrode assembly of a solid polymer

electrolyte fuel cell according to claim 5, wherein said electrolyte membrane includes a

first polymer ion-exchange component, and each of said air pole and said fuel pole

includes a second polymer ion-exchange component and said catalyst particles,

wherein said second polymer ion-exchange component is a sulfonated substance of

aromatic hydrocarbon polymer free of fluorine which is soluble when said electrolyte

membrane/electrode assembly is immersed into a solvent for recovering said catalyst

particles, and said first polymer ion-exchange component is a sulfonated substance of

aromatic hydrocarbon polymer free of fluorine which is soluble when an undissolved material removed from said solvent is immersed into a solvent for recovering said first polymer ion-exchange component.

7. (added) An electrolyte membrane/electrode assembly of a solid polymer

B | electrolyte fuel cell according to claim 6, wherein the solubilities of said first and second polymer ion-exchange components in said solvent into which said electrolyte membrane/electrode assembly is immersed are such that the solubility of said second polymer ion-exchange component is larger than that of said first polymer ion-exchange component.

8. (added) An electrolyte membrane/electrode assembly of a solid polymer

electrolyte fuel cell according to claim 5, 6 or 7, wherein said aromatic hydrocarbon polymer is any of polyether-ether ketone, polyether sulfone, polysulfone, polyetherimide, polyphenylene sulfide and polyphenylene oxide.

